

What is claimed is:

1. (*Currently Amended*) A thermoplastic polyurethane composition, comprising:
 - the reaction product of
 - a polyester polyol having a number average of molecular weight of from about 500 to about 5,000;
 - from about ~~2~~ 5 to about ~~25~~ 20 parts by weight of a polyether co-polyol comprising poly(tetramethylene ether glycol) per 100 parts by weight of the combined total amount of said polyester polyol and said polyether co-polyol;
 - a diisocyanate having the formula $R(NCO)_n$ where n is an integer of 2 and R is an aromatic, cycloaliphatic, aliphatic, or combinations thereof having from 2 to 20 carbon atoms;
 - a symmetrical chain extender selected from the group consisting of 1,6-hexanediol, 1,3-propanediol, 1,5-pentanediol, 1,4-butanediol, 1,4-cyclohexanedimethanol (CHDM), hydroquinone di(β -hydroxyethyl)ether (HQEE), 1,4-benzenedimethylol, and combinations thereof;
 - from about ~~2~~ 5 to about ~~25~~ 10 moles of a co-chain extender selected from the group consisting of 1,3-butanediol, neopentylglycol, dipropylene glycol, diethylene glycol, di(β -hydroxyethyl) resorcinol, 1,2-propylene glycol, and combinations thereof per 100 moles of said symmetrical chain extender;
 - the ratio of the molar percent of said co-chain extender to said symmetrical chain extender to weight percent of said polyether co-polyol to the combined total weight of said polyester polyol and said polyether co-polyol, being from about ~~0.15~~ 0.2 to about ~~3~~ 2.

2. *(Previously Presented)* A thermoplastic polyurethane composition according to claim 1, wherein said reaction product has a reduced annealing value, V_t , of about 4.0 or less and a sensitivity of the complex viscosity to temperature $V_R ((T_m+15)/(T_m+35))$ of about 9 or less.

3. *(Previously Presented)* A thermoplastic polyurethane composition according to claim 2, wherein said reaction product has a sensitivity to shear V_f at $T_m+15^\circ\text{C}$ of about 10 or less or a V_f at $T_m+35^\circ\text{C}$ of about 5 or less.

4. *(Previously Presented)* A thermoplastic polyurethane composition according to claim 3, wherein the number average molecular weight of said polyester polyol is from about 600 to about 4,000; and

wherein the number average molecular weight of said polyether co-polyol is from about 500 to about 4,000, and

wherein said reaction product has a hydrolytic stability, TS_N , of about 0.3 or greater.

Claim 5 *(Cancelled)*.

6. *(Previously Presented)* A thermoplastic polyurethane composition of claim 4 wherein said co-chain extender is neopentylglycol, dipropylene glycol, 1,3-butanediol, or mixtures thereof.

7. *(Previously Presented)* A thermoplastic polyurethane composition according to claim 6, wherein said reduced annealing value V_t is about 3.5 or less, wherein said V_f at $T_m+15^\circ\text{C}$ is about 6 or less, and said V_f at $T_m+35^\circ\text{C}$ is about 4 or less, wherein said polyether co-polyol is poly(tetramethylene ether glycol), wherein said diisocyanate is MDI or H_{12} MDI, or combinations thereof, wherein said symmetrical chain extender is 1,4-butanediol; and

wherein said co-chain extender is 1,3-butanediol, neopentylglycol, or dipropylene glycol.

Claim 8-9 (*Cancelled*).

10. (*Original*) A thermoplastic polyurethane composition according to claim 7, wherein said polyester polyol is derived from adipic acid, suberic acid, sebacic acid, or azelaic acid, or combinations thereof with 1,4-butanediol, 1,6-hexanediol, neopentyl glycol, diethylene glycol, or combinations thereof.

Claims 11-12 (*Cancelled*).

13. (*Previously Presented*) A thermoplastic polyurethane composition of claim 1 wherein at least four of the following six (A through F) criteria are met:

- A. a reduced crystallinity expressed as T_{CN} is 0.95 or less,
- B. an improved hydrolytic stability expressed as TS_N is 0.3 or greater,
- C. a reduced sensitivity to shear expressed as $V_f(T_m + 15)$ is 10 or less,
- D. a reduced sensitivity to shear expressed as $V_f(T_m + 35)$ is 5 or less,
- E. a sensitivity of the complex viscosity to temperature expressed as V_R is 10 or less,

and

- F. a reduced annealing expressed as V_I is 4 or less.

14. (*Original*) The thermoplastic polyurethane composition of claim 13 wherein at least five of the criteria (A through F) are met.

15. (*Original*) The thermoplastic polyurethane composition of claim 14 wherein all six of the criteria (A through F) are met.

16. *(Original)* The thermoplastic polyurethane composition of claim 13 wherein T_{CN} is 0.85 or less, T_{SN} is 0.35 or greater, $V_f(T_m + 15)$ is 6 or less, $V_f(T_m + 35)$ is 4 or less, V_R is 9 or less, and V_t is 3.5 or less.

17. *(Original)* The thermoplastic polyurethane composition of claim 16 wherein at least five of the criteria are met.

18. *(Original)* The thermoplastic polyurethane composition of claim 17 wherein all six of the criteria are met.

19. *(Original)* A coated fabric wherein said coating comprises the thermoplastic polyurethane composition of claim 1.

20. *(Original)* A coated fabric wherein said coating comprises the thermoplastic polyurethane composition of claim 13.

21. *(Original)* A coated fabric wherein said coating comprises the thermoplastic polyurethane composition of claim 16.

22. *(Original)* A coated fabric wherein said coating comprises the thermoplastic polyurethane composition of claim 16, and wherein said fabric comprises nylon, polyester, or polyolefin.

23. *(Original)* A sheet or a film comprising the thermoplastic polyurethane composition of claim 1.

24. *(Original)* A sheet or a film comprising the thermoplastic polyurethane composition of claim 13.

25. *(Original)* A sheet or a film comprising the thermoplastic polyurethane composition of claim 16.

26. *(Original)* A sheet or film comprising the thermoplastic polyurethane composition of claim 17.

27. *(Original)* A conveyor belt comprising the thermoplastic polyurethane composition of claim 1.

28. *(Original)* A conveyer belt comprising the thermoplastic polyurethane composition of claim 13.

29. *(Original)* A conveyer belt comprising the thermoplastic polyurethane composition of claim 16.

30. *(Original)* A conveyer belt comprising the thermoplastic polyurethane composition of claim 17.

31. *(Original)* An inflatable article, an apparel, or a storage bag comprising the thermoplastic polyurethane composition of claim 1.

32. *(Original)* An inflatable article, an apparel, or a storage bag comprising the thermoplastic polyurethane composition of claim 13.

33. *(Original)* An inflatable article, an apparel, or a storage bag comprising the thermoplastic polyurethane composition of claim 16.

34. *(Original)* An inflatable article, an apparel, or a storage bag comprising the thermoplastic polyurethane composition of claim 17.

35. *(Currently Amended)* A process for producing a thermoplastic polyurethane polymer comprising reacting:

- A. a polyester polyol having a number average molecular weight of from about 500 to about 5,000;
- B. from about ~~2~~ 5 to about ~~25~~ 20 parts by weight of a polyether co-polyol comprising poly(tetramethylene ether glycol) per 100 parts by weight of the combined total amount of said polyester polyol and said polyether co-polyol;
- C. a diisocyanate;
- D. a symmetrical chain extender selected from the group consisting of 1,6-hexanediol, 1,3-propanediol, 1,5-pentanediol, 1,4-butanediol, 1,4-cyclohexanedimethanol (CHDM), hydroquinone di(β -hydroxyethyl)ether (HQEE), 1,4-benzenedimethylol, and combinations thereof;
- E. from about ~~2~~ 5 to about ~~25~~ 10 moles of a co-chain extender selected from the group consisting of 1,3-butanediol, neopentyl glycol, dipropylene glycol, diethylene glycol, di(β -hydroxyethyl) resorcinol, 1,2-propylene glycol, and combinations thereof per 100 moles of said symmetrical chain extender; and

wherein the ratio of the molar percent of said co-chain extender to said symmetrical chain extender to weight percent of said polyether co-polyol to the combined total weight of said polyester polyol and said polyether co-polyol, is from about ~~0.15~~ 0.2 to about ~~3~~ 2.

36. *(Previously Presented)* The process of claim 35 further comprising a thermoplastic polyurethane catalyst in an amount less than about 1000 parts by weight per million parts by weight of the combined weight of said polyester polyol, polyether co-polyol, diisocyanate, symmetrical chain extender and said co-chain extender.

37. *(Previously Presented)* The process of claim 36 wherein said process is conducted in a twin screw extruder where the reactants are brought together and reacted.

38. *(Original)* The process of claim 37 wherein said process is conducted at from about 110°C to about 200°C.

39. *(Original)* The process of claim 38 wherein the reaction time is from about 2 to about 3 minutes.

Claims 40-41 *(Cancelled)*.

42. *(Previously Presented)* The process of claim 35

wherein said polyester polyol is derived from an acid selected from the group consisting of adipic acid, suberic acid, sebacic acid, azelaic acid, and combinations thereof reacted with a glycol selected from the group consisting of 1,4-butanediol, diethylene glycol, 1,6-hexanediol, neopentyl glycol and combinations thereof.